

PRODUCT TEST RESULTS



PROSOCO® SingleStep® WB

TEST	METHOD	SUBSTRATES/CRITERIA	RESULTS
Concrete Curing	AASHTO M-148	Type 1, Classes A & B	Meets Requirements
	ASTM C309	Type 1, Classes A & B	Meets Requirements
Dry Time	ASTM C309	<4 hours	1.5 hours
Water Retention	ASTM C156	<0.55 kg/m ²	0.46 kg/m ²
Reflectance	ASTM E1347	Reflectance - Type II, >60%	67%
Chloride Ion Resistance	NCHRP 244 Series II	Concrete - Reduction in Chloride Absorption	90%
	NCHRP 244 Series IV	Concrete - Reduction in Chloride Absorption	88%
Slip Resistance	ANSI B101.1	Steel Troweled Concrete	>0.60
	ANSI B101.3	Steel Troweled Concrete	>0.42
Water Absorption Field Tube Test	RILEM II.4 5.0 mL, Vertical	Steel Troweled Concrete	No loss
Adhesion Pull-Off	ASTM D4541	Steel Troweled Concrete	>400 psi
Accelerated Weathering	ASTM G154 500 hours	Steel Troweled Concrete	No peeling, blistering, yellowing or chalking

Please refer to Product Data Sheet for complete application instructions. Test results are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of or a recommendation for product use. Final determination of the suitability of a product and/or procedure should be made only after thorough on-site testing on actual surfaces.

