



**AMT Laboratories**  
 3741 Greenway Circle  
 Lawrence, KS 66046  
 Phone: 888.376.3600  
 Fax: 785.830.9176

***Trenwyth Industries, Inc.***  
*Project No. 0608-18 PTP*

Two types of Trendstone® and two types of Trendstone Plus® integrally colored ground-face CMU’s with an in-plant applied acrylic finish, all with large, small and fine aggregate were submitted for testing to AMT Laboratories by PROSOCO, Inc. to determine the optimal concentration of cleaner for removal of laboratory applied mortar while limiting surface alterations to the acrylic finish. **Limiting Surface Alterations** was evaluated to determine if surface alterations are created during new construction cleaning.

**Recommendations**

Sample	New Construction Cleaning Type S Mortar (14 Day Cleaning)
“Chocolate – Trendstone Plus®”	Sure Klean® Burnished Custom Masonry Cleaner (1:2) OR (1:3)
“Dekalb Tan – Trendstone Plus®”	Sure Klean® Burnished Custom Masonry Cleaner (1:2) OR (1:3)
“Goldstone – Trendstone®”	Sure Klean® Burnished Custom Masonry Cleaner (1:2) OR (1:3)
“Graystone – Trendstone®”	Sure Klean® Burnished Custom Masonry Cleaner (1:2) OR (1:3)

Apply all products in accordance with the manufacturer’s recommendations provided on container labels and product data sheets. On-site testing should be conducted to determine the most appropriate cleaning, water repellent, or stain repellent products and procedures for a particular project. See product literature for additional application and safety information.