



Wienerberger Denmark
Helsingør, Denmark
Executive Summary
 Project No. 1905-05

Thirty-six types of brick and three types of mortar were submitted to AMT Laboratories with a request to determine the most appropriate new construction cleaner. Additionally, stain removal products suitable for clay brick were evaluated for adverse effects.

The laboratory report (1905-05 PTP Wienerberger Denmark) provides information about the products tested and descriptions of the test methods. The report includes test results as well as conclusions and recommendations. Recommendations are also provided in the chart below.

Recommendations:

Sample	New Construction Cleaning	Stain Removal (Adverse Effects)	
"PT449" Brick		MV Rust Fjerner (1:1)	
"PT450" Brick		MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)	
"PT465" Brick			
"W001" Brick			
"W103" Brick		MV Mangan Kontrol (1:6) OR MV Murvaerks Rens (1:1)	MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W105" Brick			MV Rust Fjerner (1:1) OR
"W108" Brick			MV Salt Fjerner (1:1)
"W109" Brick			MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)

Apply all products in accordance with the manufacturer's recommendation provided on container labels and product data sheets. On-site testing should be conducted to determine the most appropriate product and procedures for a particular project. See product literature for additional application and product information.



Wienerberger Denmark
Helsingør, Denmark
Executive Summary
 Project No. 1905-05

Recommendations: (cont.)

Sample	New Construction Cleaning	Stain Removal (Adverse Effects)	
"W110" Brick	MV Mangan Kontrol (1:6) OR MV Murvaerks Rens (1:1)	MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)	
"W112" Brick			
"W170" Brick			
"W193" Brick			
"W209" Brick			
"W212" Brick			
"W309" Brick			
"W409" Brick		MV Rust Fjerner (1:1) MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)	
"W445" Brick			MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W447" Brick			
"W451" Brick			MV Rust Fjerner (1:1)
"W452" Brick			
"W453" Brick			
"W454" Brick			
"W466" Brick			MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W470" Brick			

Apply all products in accordance with the manufacturer's recommendation provided on container labels and product data sheets. On-site testing should be conducted to determine the most appropriate product and procedures for a particular project. See product literature for additional application and product information.



Wienerberger Denmark
Helsingør, Denmark
Executive Summary
 Project No. 1905-05

Recommendations: (cont.)

Sample	New Construction Cleaning	Stain Removal (Adverse Effects)
"W479" Brick	MV Mangan Kontrol (1:6) OR MV Murvaerks Rens (1:1)	MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W490" Brick		MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W491" Brick		MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W492" Brick		MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W494" Brick		MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W495" Brick		MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W496" Brick		MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"W498" Brick		MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"Veldbrons" Brick		MV Salt Fjerner (1:1)
"Bronsdroen" Brick		MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"Blau Wrood" Brick		MV Mangan Fjerner (1:3) OR MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)
"Vigo Rosa" Brick		MV Rust Fjerner (1:1) OR MV Salt Fjerner (1:1)

Apply all products in accordance with the manufacturer's recommendation provided on container labels and product data sheets. On-site testing should be conducted to determine the most appropriate product and procedures for a particular project. See product literature for additional application and product information.