

PRODUCT TEST RESULTS

R-Guard Joint & Seam Filler



PROSOCO

ICC-ES AC212¹: ACCEPTANCE CRITERIA FOR WATER-RESISTIVE COATINGS USED AS WATER-RESISTIVE BARRIERS OVER EXTERIOR SHEATHING (*JOINT & SEAM FILLER TESTED AS PART OF AN ASSEMBLY)

TEST	METHOD	CRITERIA	RESULTS
*Tensile Bond	ASTM C 297	Minimum 15 psi (105 kPa)	Pass
*Freeze-Thaw	ICC-ES AC212	No cracking, checking, crazing, erosion, delamination or other deleterious effects	Pass
*Water Resistance	ASTM D 2247	No cracking, checking, crazing, erosion, delamination, or other deleterious effects	Pass
*Water Penetration	ASTM E 331	No visible water penetration at sheathing joints as viewed from back of the panel	Pass
*Structural, Racking, Restrained Environmental Conditioning & Water Penetration	ASTM E 1233A ASTM E 72 ICC-ES AC212 ASTM E 331	No cracking of the coating	Pass
*Weathering	ICC-ES AC212 AATCC ² 127	No cracking of the coating; no water penetration	Pass

ABAA: AIR BARRIER ASSOCIATION OF AMERICAN ACCEPTANCE CRITERIA FOR LIQUID APPLIED MEMBRANES (*JOINT & SEAM FILLER TESTED AS PART OF AN ASSEMBLY)

*Air Leakage of Air Barrier Assemblies	ASTM E 2357	≤ 0.2 L / s·m ² at 75 Pa (≤ 0.04 cfm / ft ² at 1.57 psf)	Pass 0.0105 / s·m ² at 75 Pa (0.0021 cfm / ft ² at 1.57 psf)
--	-------------	---	---

FIRE TESTING (*JOINT & SEAM FILLER TESTED AS PART OF AN ASSEMBLY)

*Fire Propagation Characteristics of Exterior Non-load-bearing Wall Assemblies	NFPA ³ 285	Must resist flame propagation and flame spread	Pass ⁴
Surface Burning Characteristics	ASTM E 84	Criteria for ICC and NFPA Class A Building Material Flame Spread ≤ 25 Smoke Developed ≤ 450	Meets Class A Building Material Flame Spread: 15 Smoke Developed: 5

All testing was completed by independent, accredited laboratories.

NOTES:

1. International Code Council Evaluation Service Acceptance Criteria 212
2. American Association of Textile Chemists and Colorists
3. National Fire Protection Association
4. Southwest Research Institute Report No. 01.17421.01.001

