



AMT Laboratories • 3741 Greenway Circle • Lawrence, Kansas 66046 • (888) 376-3600

## Sure Klean® Weather Seal Gloss 'N Guard WB Stain Resistance Testing Summary

For PROSOCO, Inc,  
August 2022

### TEST METHODS: Stain Resistance – ASTM D 1308 (Modified)

The soiling agents were allowed to dwell on the treated and untreated substrates for times of 4 hours, 1 hour, and 10 minutes. The test areas were then cleaned with Enviro Klean® Klean 'N Release diluted with ten parts water and scrubbed under a stream of running water. The samples were allowed to dry for 24 hours. Evaluation consisted of a visual examination of the tested areas to determine the percentage of staining removal.

### TEST RESULTS:

#### Limestone

% Removal

Untreated Control							
	Cola	Ketch.	Must.	Red Wine	Bals. Vin.	Soy Sauce	Coffee
4 hour	100%	80%	70%	100%	30%	70%	70%
1 hour	100%	90%	80%	100%	40%	80%	90%
10 min.	100%	90%	90%	100%	50%	90%	90%
Sure Klean® Weather Seal Gloss 'N Guard WB							
	Cola	Ketch.	Must.	Red Wine	Bals. Vin.	Soy Sauce	Coffee
4 hour	100%	100%	100%	100%	100%	100%	100%
1 hour	100%	100%	100%	100%	100%	100%	100%
10 min.	100%	100%	100%	100%	100%	100%	100%

% Removal of stain following maintenance cleaning.

\* Indicates etching of surface treatment due to the acidic nature of the staining agent.

**TEST RESULTS (cont.):**

**Sandstone**

% Removal

<b>Untreated Control</b>							
	<b>Cola</b>	<b>Ketch.</b>	<b>Must.</b>	<b>Red Wine</b>	<b>Bals. Vin.</b>	<b>Soy Sauce</b>	<b>Coffee</b>
<b>4 hour</b>	100%	100%	80%	30%	90%	80%	80%
<b>1 hour</b>	100%	100%	90%	50%	100%	100%	100%
<b>10 min.</b>	100%	100%	100%	100%	100%	100%	100%
<b>Sure Klean® Weather Seal Gloss 'N Guard WB</b>							
	<b>Cola</b>	<b>Ketch.</b>	<b>Must.</b>	<b>Red Wine</b>	<b>Bals. Vin.</b>	<b>Soy Sauce</b>	<b>Coffee</b>
<b>4 hour</b>	100%	100%	100%	100%	100%	100%	100%
<b>1 hour</b>	100%	100%	100%	100%	100%	100%	100%
<b>10 min.</b>	100%	100%	100%	100%	100%	100%	100%

**Concrete Pavers**

% Removal

<b>Untreated Control</b>							
	<b>Cola</b>	<b>Ketch.</b>	<b>Must.</b>	<b>Red Wine</b>	<b>Bals. Vin.</b>	<b>Soy Sauce</b>	<b>Coffee</b>
<b>4 hour</b>	100%	100%	100%*	50%	80%	90%	<1%
<b>1 hour</b>	100%	100%	100%	100%	100%	100%	100%
<b>10 min.</b>	100%	100%	100%	100%	100%	100%	100%
<b>Sure Klean® Weather Seal Gloss 'N Guard WB</b>							
	<b>Cola</b>	<b>Ketch.</b>	<b>Must.</b>	<b>Red Wine</b>	<b>Bals. Vin.</b>	<b>Soy Sauce</b>	<b>Coffee</b>
<b>4 hour</b>	100%	100%	100%	100%	100%	100%	100%
<b>1 hour</b>	100%	100%	100%	100%	100%	100%	100%
<b>10 min.</b>	100%	100%	100%	100%	100%	100%	100%

% Removal of stain following maintenance cleaning.

\* Indicates etching of surface treatment due to the acidic nature of the staining agent.

**See AMT Laboratories report "2203-02 SR" for full testing information.**

Jobsite testing should always be conducted in a small, inconspicuous location prior to overall application of any product. Application procedures from the PROSOCO, Inc. Product Data Sheet instructions must be followed.



Courtney A. Murdock, CDT, APT RP  
 Director of Project Testing