CMU/CIP Concrete Rough Opening -C1.1

AIR & WATER BARRIERS

CMU/Cast-in-Place Concrete Wall Construction


Field of wall -- Fill small voids and cracks (up to 1/2-inch) in the CMU surface with **FastFlash or Joint & Seam Filler**. Use a dry joint knife or trowel to press and spread 1 inch beyond each side to a thickness of 20-30 mils.

Repair larger cracks or voids with mortar.

R•Guard

Best practice rough opening -- Apply a thick bead of **FastFlash** in each corner and in a zigzag pattern over the concrete block inside the rough opening and wall face surrounding the rough opening. Use a dry joint knife, trowel or chipper brush to spread the wet product to protect the rough opening with a seamless flashing membrane that extends no more than 1 inch over the face of the wall. Apply additional **FastFlash** as needed to create an opaque, monolithic

flashing membrane free of voids or pinholes. Allow to skin over.



Wood buck -- If wood bucks are not already installed, apply two thick beads of **FastFlash** or **Joint & Seam Filler** along the perimeter faces of the wood buck before attaching it to the structure while still wet. Install anchor bolts.

After installation of wood buck, spot and cover the installed heads of the anchor bolts. Apply a thick bead of **FastFlash** or **Joint & Seam Filler** to all inside corners of the wood buck. Use a dry joint knife or trowel to press and spread 1 inch beyond each side to a thickness of 20-30 mils.

Apply a thick bead of **FastFlash** or **Joint & Seam Filler** to the perimeter joint between the wood buck and the CMU wall. Use a dry trowel or spatula to tool and seal the joint. Create a profile that directs bulk water away from the joint. Allow **Joint & Seam Filler** to skin over.